

INFORMATIVE

Max. working pressure	MPa	13		
Max. working temperature	°C	Continual	400	steam 350
		Peak	450	

Application: water, water vapour, gas, oil, alcohols, fuel, basic chemicals, cooling liquid

TECHNICAL PARAMETERS

TECHNICAL PARAMETERS			Corresponding standard	Testing acc. to TP 62-085-15
DENSITY	g.cm ⁻³	1,7 – 2,0	DIN 28 090 - 2	
RESIDUAL STRESS* 16 h/175/300 °C	MPa	32/25	DIN 52 913	
RESIDUAL STRESS* 16 h/300 °C		25	BS 7531	
COMPRESSIBILITY	%	5 – 15	ASTM F 36 J	
RECOVERY	min. %	60	ASTM F 36 J	
SPEC. LEAKAGE RATE	≈ mg/(s.m)	0,02	DIN 3535 – 6	
FLUID RESISTANCE – THICKNESS CHANGE				
ASTM OIL - IRM 903, ČSN ISO 1817 5 h/150 °C	max. %	3	ASTM F 146	
ASTM FUEL B - ČSN ISO 1817 5 h/23 °C	max. %	5	ASTM F 146	
FLEXIBILITY	no cracks and breaks		ASTM F 147	
COLOR AND PRINTING	BLUE – branded on one side TEMASIL TITAN DIN 28 091 – 2 FA-MAZ-0 ASTM F 104 F 712 112 M5 BS 7531 GRADE AX			

Note:

- a) parameters are valid for thickness 2,0 mm
- b) * value valid for thickness 1,5 mm

CERTIFICATION:

TA Luft



Společnost je zapsána v obchodním rejstříku vedeném u Městského soudu v Praze, oddíl B, vložka 373, IČO 00012092

Temac a.s. company is incorporated in companies register with Municipal Court in Prague, section B, insert 373, Incorporation No. 00012092

Code: wdb33

Page: 1 of 1

Approved: 27.4.2015

Valid since: 28.4.2015

www.temac.cz

Interference with this document is prohibited.